



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2183032 C 2001/07/17

(11)(21) **2 183 032**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1996/08/09

(41) Mise à la disp. pub./Open to Public Insp.: 1998/02/10

(45) Date de délivrance/Issue Date: 2001/07/17

(51) Cl.Int.⁶/Int.Cl.⁶ B26F 1/38

(72) Inventeur/Inventor:

HRUSCHAK, Lawrence Alexander, CA


(73) Propriétaire/Owner:

I.S.I. CANADA INC., CA

(74) Agent: THOMPSON, DOUGLAS B.

(54) Titre : PROCÉDE DE REALISATION DE FENTES DANS DES TUYAUX METALLIQUES

(54) Title: METHOD FOR MAKING SLOTS IN METAL PIPE



(57) Abrégé/Abstract:

A method for making slots in metal pipe and, in particular, slots less than 15 thousandths of an inch in width. Firstly, providing a metal pipe having an exterior surface and an interior surface which defines an axially extending interior bore. Secondly, cutting an axially extending elongate slot having a width that is larger than desired in the pipe with a cutting tool. The slot extends through the pipe providing fluid communication from the exterior surface to the interior surface. The slot has longitudinal peripheral edges. Thirdly, applying pressure to the exterior surface of the pipe along at least one of the longitudinal peripheral edges of the slot until the metal pipe is deformed sufficiently to close the slot to a desired width.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cipo.gc.ca>

OPIC • CIP0 191

OPIC



CIP0

2183032

ABSTRACT OF THE DISCLOSURE

A method for making slots in metal pipe and, in particular, slots less than 15 thousandths of an inch in width. Firstly, providing a metal pipe having an exterior surface and an interior surface which defines an axially extending interior bore. Secondly, cutting an axially extending elongate slot having a width that is larger than desired in the pipe with a cutting tool. The slot extends through the pipe providing fluid communication from the exterior surface to the interior surface. The slot has longitudinal peripheral edges. Thirdly, applying pressure to the exterior surface of the pipe along at least one of the longitudinal peripheral edges of the slot until the metal pipe is deformed sufficiently to close the slot to a desired width.

2183032

1

TITLE OF THE INVENTION:

method for making slots in metal pipe

5

NAME OF INVENTOR:

Lawrence Alexander Hruschak

10

FIELD OF THE INVENTION

The present invention relates to a method for making slots
in metal pipe and, in particular, slots less than 15
15 thousandths of an inch in width.

BACKGROUND OF THE INVENTION

20 The oil industry uses slotted metal pipe as a screening
mechanism when drilling for heavy oil. Heavy oil is commonly
found in oil bearing sand formations. Oil wells are drilled
that have horizontal sections, which can be 1000 meters or more
in length. These horizontal sections have a tendency to
25 collapse and become filled with sand. In order to prevent this
from occurring, slotted metal pipe is placed in the horizontal
sections. The sand is supported by the metal pipe, while the
heavy oil seeps through the slots into the pipe where it can
be pumped to surface.

30

It is not unusual for the slots to have a width of between
25 and 15 thousandths of an inch. Even with slots of that
width, some sand enters the pipe. In order to further restrict
the entry of sand into the pipe, the industry is demanding
35 slots of less than 15 thousandths of an inch. It has yet to
be determined how small the slots can be without unduly
restricting the rate of flow into the pipe. It has been

2183032

2

speculated that between 5 and 7 thousandths of an inch will be optimum. Unfortunately, most slot cutting equipment is unable to cut slots with a width of less than 15 thousandths of an inch.

5

SUMMARY OF THE INVENTION

What is required is a method for making slots in metal pipe that is better suited for making slots less than 15
10 thousandths of an inch in width.

According to the present invention there is provided a method for making slots in metal pipe. Firstly, providing a metal pipe having an exterior surface and an interior surface
15 which defines an axially extending interior bore. Secondly, cutting an axially extending elongate slot having a width that is larger than desired in the pipe with a cutting tool. The slot extends through the pipe providing fluid communication from the exterior surface to the interior surface. The slot
20 has longitudinal peripheral edges. Thirdly, applying pressure to the exterior surface of the pipe along at least one of the longitudinal peripheral edges of the slot until the metal pipe is deformed sufficiently to close the slot to a desired width.

25 With the method, as described above, short comings in cutting equipment are overcome by applying pressure until the material surrounding the slot yields to narrow the slot to a desired width. There are a variety of ways that this can be done. A preferred manner of applying pressure is by means of
30 a roller.

BRIEF DESCRIPTION OF THE DRAWINGS

35 These and other features of the invention will become more apparent from the following description in which reference is made to the appended drawings, wherein:

FIGURE 1 is a side elevation view, in cut away section, of a pipe which is in the process of being slotted in accordance with the teachings of the present method.

FIGURE 2 is a side elevation view, in cut away section, of a slot in the pipe illustrated in FIGURE 1, being treated by a pressure roller.

FIGURE 3 is a side elevation view, in cut away section, of a pipe that has been slotted in accordance with the teachings of the present method.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The preferred method for making slots less than 15 thousandths of an inch in width in metal pipe will now be described with reference to FIGURES 1 through 3.

Referring to FIGURE 1, firstly, provide a metal pipe 10 having an exterior surface 12 and an interior surface 14 which defines an axially extending interior bore 16. Secondly, cut an axially extending elongate slot 18 having a width that is larger than desired in metal pipe 10 with a cutting tool (not shown). The cutting tool can take various forms from milling machines to lasers. Slot 18 extends through pipe 10 providing fluid communication from exterior surface 12 to interior surface 14. Slot 18 has longitudinal peripheral edges 20 and 22. To this point the steps involved in the preferred method do not materially differ from the steps taken in the prior art. In the prior art, slot 18 would be cut precisely to the desired width. With the present method, slot 18 is deliberately cut having a width that is larger than desired, as a preliminary step in the method.

Referring to FIGURE 2, thirdly, applying pressure to exterior surface 12 of pipe 10 along one or both of longitudinal peripheral edges 20 and 22 of slot 18 until metal pipe 10 is deformed sufficiently to close slot 18 to a desired

width. The key to the present method is to apply pressure that exceeds the yield strength of the material to narrow the slot. There are a variety of means by which this may be done. For example, by means of a stamp or punch, by means of a seaming tool. The preferred manner of applying pressure, however, is by means of a roller 24, as illustrated. The use of roller 24 has a number of advantages. Roller 24 can be equipped with a guide flange 26 that centers roller 24 in slot 18 and limits the deformation of the material when pressure is applied. The pressure on roller 24 can be regulated more easily than other methods. Roller 24 can be shaped with sloping contact surfaces 28 that help localize the pressure along longitudinal peripheral edges 20 and 22 to achieve the desired deformation. Roller 24 is viewed as being more readily incorporated into mechanized slot cutting equipment.

Referring to FIGURE 3, there is illustrated slot 18 after it has been narrowed by roller 24. The resulting slot 18 has desirable properties for the intended screening application. It has a narrow opening 30 of 5 thousandths of an inch at exterior surface 12. Past opening 30 it has an enlarged portion 32 of 15 thousandths of an inch or wider. This is desirable as grains of sand fine enough to temporarily wedge into narrow opening 30 will tend to be pushed by pressure through enlarged portion 32 into interior bore 16 of pipe 10, rather than blocking off slot 18. Enlarged portion 32 also results in a decrease in pressure loss across narrow opening 30 of slot 18.

It will be apparent to one skilled in the art that modifications may be made to the illustrated embodiment without departing from the spirit and scope of the invention as hereinafter defined in the Claims.

2183032

5

**THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY
OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:**

- 5 1. A method for making slots in metal pipe, comprising the steps of:
- firstly, providing a metal pipe having an exterior surface and an interior surface which defines an axially extending interior bore;
- 10 secondly, cutting an axially extending elongate slot having a width that is larger than desired in the pipe with a cutting tool, the slot providing fluid communication from the exterior surface to the interior surface, the slot having longitudinal peripheral edges; and
- 15 thirdly, applying pressure to the exterior surface of the pipe along at least one of the longitudinal peripheral edges of the slot until the metal pipe is deformed sufficiently to close the slot to a desired width.
- 20 2. The method as defined in Claim 1, having pressure applied by a roller.
3. The method as defined in Claim 2, the roller having a centering and a deformation controlling guide flange.
- 25 4. The method as defined in Claim 1, having pressure applied to each of the longitudinal peripheral edges of the slot.

2183032




FIGURE 1




FIGURE 2




FIGURE 3